



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 291 208  
A3**

(12)

# EUROPEAN PATENT APPLICATION

(21) Application number: 88303919.0

(51) Int. Cl.<sup>5</sup>: C08G 61/08, C08F 210/02,  
C08L 23/08, C08L 65/00

(22) Date of filing: 29.04.88

(30) Priority: 01.05.87 JP 106354/87  
08.05.87 JP 110630/87

(43) Date of publication of application:  
17.11.88 Bulletin 88/46

(64) Designated Contracting States:  
AT BE CH DE ES FR GB GR IT LI LU NL SE

(69) Date of deferred publication of the search report:  
11.07.90 Bulletin 90/28

(71) Applicant: MITSUI PETROCHEMICAL  
INDUSTRIES, LTD.  
2-5, Kasumigaseki 3-chome Chiyoda-ku  
Tokyo 100(JP)

(72) Inventor: Minami, Syuji  
2-2 Misono 1-chome  
Ootake-shi Hiroshima(JP)  
Inventor: Kawamoto, Keiji  
30-6 Ajina 4-chome  
Hatsukaichi-shi Hiroshima(JP)  
Inventor: Todo, Akira  
5 Yushudainishi 2-chome  
Ichihara-shi Chiba(JP)  
Inventor: Kuroiwa, Toshiaki  
4-2 Wakicho, waki 2-chome  
Kuga-gun Yamaguchi(JP)  
Inventor: Kasai, Tetsuzi  
4-3 Wakicho, Waki 2-chome  
Kuga-gun Yamaguchi(JP)

(74) Representative: Myerscough, Philip Boyd et al  
J.A.Kemp & Co. 14, South Square Gray's Inn  
London, WC1R 5EU(GB)

(54) Cycloolefin type random copolymer compositions and uses thereof.

(57) Compositions comprising (A) cycloolefin random copolymer containing an ethylene component, and a cycloolefin component represented by the general formula [I] or [II] and having an intrinsic viscosity of 0.05-10 dl/g as measured at 135 °C in decalin and a softening temperature (TMA) not lower than 70 °C, and (B) a cycloolefin random copolymer containing an ethylene component, and a cycloolefin component represented by the general formula [I] or [II] and having an intrinsic viscosity of 0.01-5 dl/g as measured at 135 °C in decalin and a softening temperature (TMA) of below 70 °C, the weight ratio of said (A) component / (B) component ranging from 100/0.1 to 100/10.

The composition is particularly useful for mold-

ing an information recording base board.

EP 0 291 208 A3



EP 88 30 3919

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
A	EP-A-0 156 464 (MITSUI PETROCHEMICAL) * Abstract * ---	1	C 08 G 61/08 C 08 F 210/02 C 08 L 23/08 C 08 L 65/00
A	EP-A-0 203 799 (MITSUI PETROCHEMICAL) * Abstract * -----	1	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			C 08 F C 08 G C 08 L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 10-04-1990	Examiner GOOVAERTS R.E.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ..... & : member of the same patent family, corresponding document			